

BROMINATED EPOXY RESINS

PRODUCT NAME	EEW / WPE (g/eq)	VISCOSITY @ 25°C (cps)	APPLICATIONS / COMMENTS
XR-18	280 - 355	Semi-solid	Semi-solid brominated epoxy resin with a bromine content of 36 - 40%.
XR-24	450 - 500	Solid	Solid brominated epoxy resin with a bromine content of 48 - 50%.
L-68	455 - 500	Solid	Solid brominated epoxy resin with a bromine content of 19 - 23%. Used with glass fabric for printed circuit board laminates conforming to NEMA FR-4 specifications.
L-247	200 - 240	350 - 450	Liquid brominated epoxy resin with a bromine content of 22 - 26%. Used for NEMA FR-5 grade electrical laminates and flame retardant applications.
L-249	320 - 410	Semi-solid	Semi-solid brominated epoxy resin with a bromine content of 46 - 50%.