

## ELECTRICAL LAMINATING SYSTEMS

<b>PRODUCT NAME</b>	<b>APPLICATIONS / COMMENTS</b>
L-67 / K-13 or 2-MI / Dicy	Recommended for G-10 laminates. L-67 is a 1-type Bis-A epoxy and K-13 is BDMA.
B-13 or L-12 / K-10 / BF <sub>3</sub> • monoethylamine	Recommended for G-11 laminates. B-13 and L-12 are Bis-A epoxies and K-10 is DDS.
L-68 / K-13 or 2-MI / Dicy	Recommended for FR-4 laminates. L-68 is a brominated epoxy and K-13 is BDMA.
L-249 or L-247 / K-10 / BF <sub>3</sub> • MEA	Recommended for FR-5 laminates. L-249 and L-247 are brominated epoxies and K-10 is DDS.