

ROYCE INTERNATIONAL

A NEW JERSEY CORPORATION

35 Carlton Avenue
East Rutherford, New Jersey 07073

Telephone: (201)438-5200
Fax: (201)438-5207
Internet Address: www.ROYCEINTL.com

Technical Data Sheet SUPER CY STABLE

Type: Phenol Blocked Polyisocyanate
Substitute to Desmodur CT Stable

Form Supplied: Solvent free product

Uses: In combination with Saturates Polyester Polyol for the formulation of
Wire enamels with especially good term heat stability of the enameled wires

Specifications:

Isocyanate content: Approx. 14%
(14.0 + 1.0%)

Color and Appearance: Yellow to brown solid lumps

Specific gravity at 30°C: 1.27 + 0.01

Flash Point: 170°C

Softening Point: 90 + 10°C

Solubility: Soluble in ketones , glycol ether, acerares phenol, Cresol etc.
Insoluble in aliphatic and aromatic hydrocarbons.

***The above information is given in good faith but without any warranty. It is required to test the product for suitability of the product in your application. Use application and processing of the product are beyond our control and entirely at your responsibility. We will try to provide you a product of consistent quality.